

## Technical data sheet

**Product name:** Bio-Flex® S 7514  
**Date of issue:** 11 February 2020

Version: 2.0

### Designation of product, preparation and manufacturer

**Trade name:** Bio-Flex® S 7514  
**Use of product:** Biodegradable polymer compound suitable for injection moulding. The biobased carbon content (BCC) is > 75 % (calculated).  
**Manufacturer:** FKUR Kunststoff GmbH  
 Siemensring 79  
 D - 47 877 Willich  
 Phone: + 49 (0) 2154 / 92 51-0  
 Fax: + 49 (0) 2154 / 92 51-51  
 Mail: info@fkur.com  
 Web: www.fkur.com

### Mechanical properties

Modulus of elasticity	3,100	[MPa]	ISO 527
Tensile strength	47	[MPa]	ISO 527
Tensile strain at tensile strength	5.7	[%]	ISO 527
Tensile stress at break	20	[MPa]	ISO 527
Tensile strain at break	14	[%]	ISO 527
Notched impact strength (Charpy), RT	3.5	[kJ/m <sup>2</sup> ]	ISO 179-1/1 eA
Impact Strength (Charpy), RT	38	[kJ/m <sup>2</sup> ]	ISO 179-1/1 eU

The values listed have been established on standardized test specimens (DIN EN ISO 3167, type A) at standard temperature and humidity conditions.

### Physical properties

Melt flow rate (190 °C/2.16 kg)	24	[g/10 min]	ISO 1133
Melting temperature	> 155	[°C]	ISO 3146-C
Vicat A softening temperature	112	[°C]	ISO 306
Heat distortion temperature HDT B	56	[°C]	ISO 75
Density	1.37	[g/cm <sup>3</sup> ]	ISO 1183

The figures should be regarded as guide values only. Under certain conditions the properties can be influenced to a significant extent by the processing conditions.

## Processing and Handling Information

### General

Bio-Flex® is a biodegradable plastic based on PLA and other biopolymers. Moisture content can lead to hydrolysis. Residual moisture content of more than 0.2 % can result in fish eyes and/or pin holes during processing.

### Drying

We recommend drying Bio-Flex® at 60°C for a period of 2 - 4 hours.

### Storage

If not specified otherwise product life is 6 month after shipment from Sellers warehouse if product is in its original packaging, stored under dry (max. 70% relative humidity) and dark conditions (not exposed to sunlight at a temperature of 5 °C to max. 30°C (ambient temperature)). It is important to observe that a major drop in external air temperature (e.g. during transportation) can result in a development of water condensate. Prior to the processing of the material, it should be ensured that there is no condensate on the packaged product.

Finished products made from Bio-Flex® must be stored dry and cold. It is recommended to wrap goods in black PE liners to protect them against moisture and UV radiation. Storage time depends on processing parameters and of climate conditions in the respective area. Because of these essential and complex interacting parameters, FKUR Kunststoff GmbH cannot give any shelf life guarantees for finished products. Please notice that the conditions mentioned above depend on experience of our customers. Each customer should execute individual storage tests according to product specifications and storage requirements.

## Technical data sheet

**Product name:** Bio-Flex<sup>®</sup> S 7514  
**Date of issue:** 11 February 2020

Version: 2.0

### Processing conditions for injection moulding

Machine equipment:	Standard screw, open nozzle.		
Machine settings:	Feeding Zone	60	[°C]
	Zone 1	130	[°C]
	Zone 2	150	[°C]
	Zone 3	170	[°C]
	Machine nozzle	180	[°C]
	Mould temperature	30 - 60	[°C]
	Holding pressure level	40 - 60	[%]
	Melt cushion (of volume)	< 10	[%]
	Cooling time	15	[s]
Max. dwell time	300	[s]	

We recommend to use cold runner systems.  
 Regrind sprues and runners can be reused at 20%.

### Purging advice for injection moulding

Before production:	Purge the plastification unit and, if existing, the hot runner with PP, PE or purging compound.
During production:	Heat tools and plastification unit to the recommended temperature. If tool is not filled, increase temperature stepwise. Material has a tendency to degrade and therefore needs a constant melt flow.
After production:	Purge the plastification unit and, if existing, the hot runner with PP, PE or purging compound.
Important information:	The dwell time of the material inside the machine shall be reduced to a minimum in order to lower the risk of degradation.

### Legal notice

Neither FKUR Kunststoff GmbH nor its marketing affiliates shall be responsible for the use of this information or of any product, method or equipment mentioned. Customers must undertake their own determination of this product's suitability and completeness for their own use, for the protection of the environment, for the health and safety of their employees and purchasers of their products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the seller's conditions of sale. The current version of General Conditions of Sale of FKUR Kunststoff GmbH is valid. The brands „FKuR – Plastics made by nature“ and “BIO-FLEX” are registered trademarks of FKUR Kunststoff GmbH, according to the international 'Nice-Classifications' (NCL9).